

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

WHAT IS CLAIMED IS:

1. A zinc-containing optical glass with a refractive index (n_d) being substantially in the range of from about 1.52 to about 1.66 and an Abbe number (v_d) being substantially in the range of from about 35 to about 54, said zinc-containing optical glass substantially comprising, on an oxide basis, the composition of:

<u>Material</u>	<u>Percentage</u> <u>by weight</u>
SiO ₂	38 - 58
ZnO	0.3 - 42
PbO	0 - <30
with ZnO+PbO	20 - 55
Li ₂ O	0 - <3
Na ₂ O	0 - 14
K ₂ O	0 - 12
with Li ₂ O+Na ₂ O+K ₂ O	≥2
F	0 - 3
MgO	0 - 6
CaO	0 - <5
SrO	0 - 6
BaO	0 - <0.9
B ₂ O ₃	0 - <1
Al ₂ O ₃	0 - <1.5
ZrO ₂	0 - <2.

00727998-13100
00727998-13100

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

2. The zinc-containing optical glass according to claim 1 and further comprising an at least one refining agent, said refining agent being in an amount indicating sufficient agent to refine said zinc-containing optical glass.

3. An optical element comprising the zinc-containing optical glass as claimed in claim 1.

4. The zinc-containing optical glass according to claim 1 with a refractive index (n_d) being substantially in the range of from about 1.54 to about 1.64 and an Abbe number (v_d) being substantially in the range of from about 40 to about 52, said zinc-containing optical glass substantially comprising, on an oxide basis, the composition of:

<u>Material</u>	<u>Percentage</u> <u>by weight</u>
SiO ₂	39 - 54
ZnO	12 - 41
PbO	6 - 22
with ZnO+PbO	31 - 52
Li ₂ O	0 - <3
Na ₂ O	0 - 13
K ₂ O	0 - 11
with Li ₂ O+Na ₂ O+K ₂ O	≥2
F	0 - 3
MgO	0 - 6

007298-1000
007037-8562260

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

CaO	0	-	<5
SrO	0	-	6
BaO	0	-	<0.9
B ₂ O ₃	0	-	<1
Al ₂ O ₃	0	-	<1.5
ZrO ₂	0	-	<2.

5. The zinc-containing optical glass according to claim 1 with a refractive index (n_d) being substantially in the range of from about 1.56 to about 1.63 and an Abbe number (v_d) being substantially in the range of from about 42 to about 52, said zinc-containing optical glass substantially comprising, on an oxide basis, the composition of:

<u>Material:</u>	Percentage
	<u>by weight</u>
SiO ₂	40 - 55
ZnO	26 - 41
PbO	1 - 16
with ZnO+PbO	31 - 48
Li ₂ O	0 - <3
Na ₂ O	0 - 12
K ₂ O	0 - 10
with Li ₂ O+Na ₂ O+K ₂ O	≥2
F	0 - 3

Docket No.: NHL-SCT-16

Variable	Mean	SD	Min	Max
Age	35.2	12.5	18	65
Gender	0.52	0.50	0	1
Marital Status	0.65	0.48	0	1
Education	12.8	2.1	9	16
Income	3200	1500	1000	8000
Health Status	0.78	0.41	0	1
Employment	0.85	0.36	0	1
Stress Level	4.2	1.8	1	7
Life Satisfaction	5.5	1.2	3	7
Resilience	6.8	1.5	4	9
Optimism	5.8	1.4	3	7
Gratitude	6.2	1.3	4	8
Self-Compassion	5.9	1.4	3	7
Emotional Regulation	6.5	1.2	4	8
Psychological Well-being	6.0	1.3	4	8
Life Purpose	6.3	1.4	4	8
Meaning in Life	6.1	1.3	4	8
Existential Well-being	6.4	1.2	4	8
Overall Quality of Life	6.6	1.1	4	8

<u>Material</u>	Percentage by weight
-----------------	-------------------------

35

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

MgO	0	- 6
CaO	0	- <5
SrO	0	- 6
BaO	0	- <0.9
B ₂ O ₃	0	- <1
Al ₂ O ₃	0	- <1.5
ZrO ₂	0	- <2.

7. A zinc-containing optical glass with a refractive index (n_d) being substantially in the range of from about 1.57 to about 1.59 and an Abbe number (v_d) being substantially in the range of from about 48 to about 52, said zinc-containing optical glass substantially comprising, on an oxide basis, the composition of:

<u>Material</u>	<u>Percentage</u> <u>by weight</u>
SiO ₂	41 - 50
ZnO	30 - 40
PbO	0 - 1
with ZnO+PbO	31 - 41
Li ₂ O	0 - <3
Na ₂ O	0 - 11
K ₂ O	0 - 10
with Li ₂ O+Na ₂ O+K ₂ O	≥2
F	0 - 3
MgO	0 - 6

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

CaO	0	-	<5
SrO	0	-	6
BaO	0	-	<0.9
B ₂ O ₃	0	-	<1
Al ₂ O ₃	0	-	<1.5
ZrO ₂	0	-	<2.

8. The zinc-containing optical glass according to claim 1 and further comprising up to about 5% by weight of one member of the group and combinations thereof: Rb₂O, La₂O₃, Y₂O₃, and GeO₂ to precisely adapt the optical properties of said zinc-containing optical glass.

9. The zinc-containing optical glass according to claim 1 and further comprising up to at most about 2.5% by weight of Cs₂O.

10. The zinc-containing optical glass according to claim 1 with the pure transmission of the glass, determined at a wavelength of 400 nm and 25 mm specimen thickness, being at least about 0.98.

11. The zinc-containing optical glass according to claim 1 and further containing up to about 8% by weight of a coloring component.

12. The zinc-containing optical glass according to claim 11 wherein said coloring component is a member of the group and combinations thereof: CuO, Cr₂O₃, CoO, Fe₂O₃, MnO, NiO, and V₂O₅.

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

13. An optical filter comprising the zinc-containing optical glass according to claim 11.

14. The zinc-containing optical glass according to claim 1 and further containing in total up to about 1% by weight of a refining agent.

15. The zinc-containing optical glass according to claim 14 wherein said refining agent is present in an amount of about 0.5% by weight.

16. The zinc-containing optical glass according to claim 15 wherein said refining agent is at least one member of the group and combinations thereof: As_2O_3 and Sb_2O_3 .

17. The zinc-containing optical glass according to claim 1 wherein the content of ZnO plus PbO is in the range of from about 21 to about 55% by weight.

18. The zinc-containing optical glass according to claim 1 wherein the total content of CaO plus SrO is in the range of from 0 to 5% by weight.

19. A method of forming zinc-containing optical glass which consists of, on an oxide basis:

<u>Material</u>	<u>Percentage</u>
	<u>by weight</u>
SiO_2	38 - 58
ZnO	0.3 - 42
PbO	0 - <30

00T02T"86622/60

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

with ZnO+PbO	20	-	55
Li ₂ O	0	-	<3
Na ₂ O	0	-	14
K ₂ O	0	-	12
with Li ₂ O+Na ₂ O+K ₂ O	≥2		
F	0	-	3
MgO	0	-	6
CaO	0	-	<5
SrO	0	-	6
BaO	0	-	<0.9
B ₂ O ₃	0	-	<1
Al ₂ O ₃	0	-	<1.5
ZrO ₂	0	-	<2

said zinc-containing optical glass having a refractive index (n_d) substantially in the range of from about 1.52 to about 1.66 and an Abbe number (v_d) substantially in the range of from about 35 to about 54, said method including the steps of:

(a) mixing and melting raw materials comprising said oxides to form a batch of glass;

(b) heating a batch of glass obtained in accordance with step (a) to produce a melt of zinc-containing optical glass;

(c) refining said melt obtained in accordance with step (b) with at least one refining agent, said refining agent being added in an amount sufficient to refine said zinc-containing

Attn: Dr. Amrhein
Dr. de Groot

Docket No.: NHL-SCT-16

optical glass.

20. The method according to claim 19 and further including the step of:

(d) homogenizing said batch of refined zinc-containing optical glass obtained in accordance with step (c).

21. The method according to claim 19 wherein said heating in accordance with step (b) is carried out at a temperature in the range of from about 1300 degrees Celsius to about 1350 degrees Celsius; and said refining in accordance with step (c) is carried out at a temperature in the range of from about 1300 degrees Celsius to about 1400 degrees Celsius.

22. The method of claim 19 wherein said refining agent is added in an amount of up to about 0.5 % by weight to said heated melt of zinc-containing optical glass obtained in accordance with step (b).

0072798-130400